

29

1005204.061102

a material layer, provided between said first semiconductor layer and said second semiconductor layer, having a thickness equal to or larger than 5 nm but equal to or smaller than 50 nm, and having a refractive index intermediate between said first and second refractive indices;

wherein said distributed Bragg reflector is tuned to a wavelength of 1.1 μm or longer.


REMARKS

Favorable consideration of the above-identified patent application in light of the foregoing amendment is respectfully requested. The present amendment corrects drawing references and other typographical/clerical errors in the specification, and amends Claim 1 to be clearer and not to narrow the claim or for any other reason related to patentability.

An early and favorable action on the merits is respectfully requested.

Respectfully submitted,

OBLON, SPIVAK, McCLELLAND,
MAIER & NEUSTADT, P.C.



Gregory J. Maier
Registration No. 25,599
Attorney of Record
Raymond C. Glenny
Registration No. 32,413

Phone (703) 413-3000
Fax (703) 413-2220



22850

I:\atty\RCG\220\220103us\220103-PreAmd.wpd

Marked-Up CopySerial No. 10/085,204Amendment Filed on: 4-1-02**ATTACHMENT****SHOWING CHANGES TO APPLICATION****IN THE SPECIFICATION***Amend page 70, lines 4-11 to read as follows:*

In the construction of Figure 20, it should be noted that the design wavelength (λ) of the distributed Bragg reflector is 1.5 μm , and the thickness of the $\text{Al}_{0.8}\text{Ga}_{0.2}\text{As}$ layer 18a and the thickness of the GaAs layer 18b are respectively chosen to 110.8 nm and [12.55] 125.5 nm so as to be equal to $\lambda/4n$, wherein n is a refractive index in the respective layers.

Amend page 110, line 19 through page 111, line 2 to read as follows:

In this embodiment, too, the heterospike buffer layer 18c of intermediate refractive index is provided in the semiconductor Bragg reflector 18 by an $\text{Al}_z\text{Ga}_{1-z}\text{As}$ ($0 \leq z < x \leq 1$) layer between the low refractive index layer 18a and the high refractive index layer 18b as already explained with reference to Figure 2. In Figure [10] 27, illustration of the heterospike buffer layer 18c will be omitted for the sake of simplicity.

Amend page 114, lines 4-11 to read as follows:

In the embodiment of Figure [10] 27, it is noted that the $GaxIn1-xPyAs1-y$ ($0 < x \leq 1$, $0 < y \leq 1$) layer 17 that acts also as an etching stopper layer is provided on the side of upper part reflector 18. Further, a similar GaInP layer 13 is provided on the lower part reflector 12.

Amend page 115, line 20 through page 116, line 3 to read as follows:

It should be noted that such a non-optical recombination elimination layer 13 or 17 constitutes a part of the semiconductor Bragg reflector 12 or 18 in any of the constitution of Figure 1 or [10] 27, and thus, the thickness thereof is set to $1/4$ the oscillation wavelength λ as measured in the medium ($\lambda/4$). It is also possible to provide such a non-optical recombination elimination layer in plural numbers.

Amend page 119, line 6 through page 120, line 8 to read as follows:

From the explanation noted above, the laser diode of Figure [10] 27 oscillates efficiently at the wavelength of $1.3 \mu m$ similarly to the case of Figure 1. The laser diode of Figure [10] 27 also has advantageous feature of small power consumption and low production cost.

The surface-emission laser diode of Figure [10] 27 can be formed also by an MOCVD process, similarly to the case of Figure

1. However, it is also possible to use an MBE process or other growth process. Further, it is possible to use nitrogen or a nitrogen compound such as NH_3 in an activated state.

Furthermore, it is possible to replace the triple quantum well structure (TQW) in the active layer 15 with another structure including different number of quantum wells such as an SQW structure, a DQW structure or an MQW structure. Further, it is possible to use a laser diode of different structure.

By adjusting the composition of the GaInNAs active layer 15a in the surface-emission laser diode of Figure [10] 1, it becomes possible to realize a surface-emission laser diode of the 1.55 μm band and further the 1.7 μm band. In the present invention, the GaInNAs active layer may contain other III-V elements such as Tl, Sb, P, and the like. Further, it is also possible to construct a surface-emission laser diode of 1.3 μm band on a GaAs substrate by using GaAsSb for the active layer.

Amend page 130, line 6 through page 133, line 9 to read as follows:

Figure [15] 32 shows an example of the semiconductor light-emitting device formed by providing such a carrier purging process. In Figure [15] 32, those parts corresponding to the parts described previously are designated by the same reference numerals and the description thereof will be omitted.

Thus, it can be seen that the Al-containing first semiconductor layer 202, the first lower part intermediate layer 601, the second lower part intermediate layer 602, the N-containing active layer 204, the upper part intermediate layer 203, and the second semiconductor layer 205 are stacked consecutively on substrate 201 in Figure [15] 32.

In forming the structure of Figure [15] 32, the crystal growth is carried out by an epitaxial growth apparatus by using an organic-metal Al source and an organic nitrogen source material. In the case, the growth interruption process is provided before the start of growth of the second lower part intermediate layer 602 but after the growth of the first lower part intermediate layer 601. During the growth interruption process, the part of the growth chamber that may make a contact with the nitrogen compound source material or the impurity in the nitrogen compound source material is purged by a hydrogen gas used as the carrier gas, such that the residual Al source material or residual Al reactant or residual Al compound or residual Al is removed.

Figure [16] 33 shows the result of measurement of the depth profile of Al concentration on a semiconductor light-emitting device in which there has been provided a growth interruption between the first lower part intermediate layer 601 and the

second lower part intermediate layer 602 and a purging process was conducted for 60 seconds.

Figure [16] 33 is referred to. It can be seen that the Al concentration in the active layer 204 is reduced to $3 \times 10^{17} \text{ cm}^{-3}$ or less as a result of such a growth interruption process and purging process. This value of Al concentration is the same degree as the Al concentration in the intermediate layers 601 and 602.

Figure [17] 34 shows the depth profile of nitrogen and oxygen for the device of Figure [15] 32.

Figure [17] 34 is referred to. It can be seen that the oxygen concentration in the active layer 204 is reduced to $1 \times 10^{17} \text{ cm}^{-3}$, which is a background level. The oxygen peak appearing in the lower part intermediate layer 601 or 602 in Figure [17] 34 is interpreted as showing oxygen segregation to the growth interruption interface as a result of interruption of growth. Thus, it is preferable to conduct the growth interruption period after the termination of the growth of the semiconductor layer containing Al but before the growth termination of the non-optical recombination elimination layer, in the case there is provided a growth interruption and purging process. In the non-optical recombination elimination layer, it is possible to increase the bandgap energy as compared with the quantum well active layer or barrier layer, and the adversary effect of the

____ • No. 2002-033590 filed on February 12, 2002,
the entire contents of which are hereby incorporated by
reference.

IN THE CLAIMS

1. (Amended) A distributed Bragg reflector, comprising:

a first semiconductor layer having a first, larger
refractive index;

a second semiconductor layer having a second, lower
refractive index,

said first and second semiconductor layers being
stacked alternately[,]; and

a material layer, provided between said first
semiconductor layer and said second semiconductor layer, having
a thickness equal to or larger than 5 nm but equal to or smaller
than 50 nm, and having a refractive index intermediate between
said first and second refractive indices; [,]

wherein said distributed Bragg reflector [being] is
tuned to a wavelength of 1.1 μm or longer[,]

wherein there is provided a material layer having a
refractive index intermediate between said first refractive index
and said second refractive index,

said material layer having a thickness equal to or
larger than 5 nm but equal to or smaller than 50 nm].

non-optical recombination caused by the oxygen segregated to the growth interruption interface is effectively suppressed when carrier injection is made into the active layer. The constitution that uses the non-optical recombination elimination layer provides a particularly advantageous effect in the case of using an active layer containing nitrogen.

In the semiconductor light-emitting device of Figure [15] 32, the impurity concentration level of Al and oxygen in the nitrogen-containing active layer 204 is reduced successfully by interrupting the growth process between the first lower part intermediate layer 601 and the second lower part intermediate layer 602 and by conducting a purging process for 60 minutes. In this way, the optical efficacy of the active layer 204 was effectively improved.

Amend page 134, lines 8-21 to read as follows:

Further, it is also possible to carry out the purging process while continuing the growth of the intermediate layer. In the constitution of Figure [10] 27, for example, the non-optical recombination elimination layer 13 is provided between the N-containing active layer 15 and the reflector 12 formed of the AlGaAs material containing Al. Thereby, the distance between the N-containing active layer 15 and the Al-containing layer is increased, and it is possible to increase

the duration of the purging process in the case the purging process is conducted simultaneously to the growth. In such a case, it is advantageous to decrease the growth rate and increase the purging time.

Amend page 304, line 18 through page 305, line 9 to read as follows:

The present application is based on Japanese priority applications

____ •No. 2001-050145 filed on February 26, 2001,
____ •No. 2001-050171 filed on February 26, 2001,
____ •No. 2001-050083 filed on February 26, 2001,
____ •No. 2001-051253 filed on February 26, 2001,
____ •No. 2001-051256 filed on February 26, 2001,
____ •No. 2001-051266 filed on February 26, 2001,
____ •No. 2001-053213 filed on February 27, 2001,
____ •No. 2001-053218 filed on February 27, 2001,
____ •No. 2001-053200 filed on February 27, 2001,
____ •No. [2001-053200] ~~2002-50548~~ filed on [February 27, 2001]

February 26, 2002,

____ •No. 2001-053190 filed on February 27, 2001,
____ •No. 2001-053225 filed on February 27, 2001,
____ •No. 2001-073767 filed on March 15, 2001,
____ •No. 2001-090711 filed on March 27, 2001,
____ •No. 2002-019748 filed on January 29, 2002,